



SJ7804

2024-01-26

2024-02-25

4.8

GB/T 16483-2008 GB/T 17519-2013

POLYESTER RESIN

SJ7804

CAS

8

241008

0553-5316333

0553-5316330

SDS

ASJ_SDS@ 126.com

[http //www.shen-jian.com](http://www.shen-jian.com)

0553-5316333

GB 13690-2009 GB 30000-2013

P261

P271

P272

P280

P302+P352

P333+P317

P342+P316

P362+P364

P410+P403

P501

vPvB

/

1

		%	GHS
	CAS: 552-30-7 EC: 209-008-0		H317- H318-

1,2,4

RESEARCH #: 01-211-422-34
Index: 607-097-0
RTEC: DC20500

8

64

H335-

15

m

/

8

“ ”

8

13

(8)

30°C (86°F)



1,2,4-

CAS. 12-377

h

TMU

[%(v/v)]
(kPa)
(=1)
(=1) 1.2
(g/cm³) 1.2 (23°C)
600 750 kg/m3
(mg/L)

(mg/L)
(°C) 350
(°C) 350

(°C) 350

VOC

(7)

()

1,2,4			

CAS 552-30

3

9

/ (Koc)

и6-K •™ñ0 SFUHIP'™-@ @

G-Đ

	—	—	—

MARPOL 73/78 II IBC

--

	A	B	C	D	E	F	G	H	I	J	K

A				2015			2015	92			
B			2022				2022	8			
C							2019	60			
D				(1 2)			2011	95		2013	12
E					445	2016		666			
F											
G								2020	1		
H							2017	83		2020	47
I			2017			2017	05	11			
J			(2019)			2019	07	05			
K			(2023)							2022	12 29 28

	AIIC	DSL	DRAFT	EINECS	ENCS	IECSC	KECL	NCI	INSQ	NZloc	PICCS
	TCSI	TSCA									

- AIIC
- DSL
- DRAFT
- EINECS
- ENCS
- IECSC
- KECL
- NCI
- INSQ
- NZloc
- PICCS
- TCSI
- TSCA TSCA

	A	B	C	D	E

A

B

A B C E

C

D

“ ” PIC

E

UNECE

2 9 15

2024 02 25

2021 06 28

4.8

1 (ICSC), <http://www.ilo.org/dyn/icsc/showcard.home>

2 <http://www.iarc.fr/>

3 OECD <http://www.echemportal.org/echemportal/index?page>

4 CAMEO <http://cameochemicals.noaa.gov/search/simple>

5 : <http://chem.sis.nlm.nih.gov/chemidplus/chemidlite.jsp>

6 <http://cfpub.epa.gov/iris/>

7 <http://www.phmsa.dot.gov/hazmat/library/erg>

8 GESTIS- <http://gestis-en.itrust.de/>

CAS–

TSCA– TSCA

PC-STEL–

PC-TWA–

DNEL–

IARC–

RPE–

PNEC–

LC₅₀– 50%LD₅₀–50%

NOEC–

EC₅₀–50%

PBT–

POW– /

BCF– (BCF)

vPvB–

CMR–

IMDG–

